





Datasheet Rubber components

Technical specifications

Technische specifications rubber components			
Material	Recycled rubber		
Thermal stability long-term	-40°C up to +80°C		
Thermal stability short-term	up to +110°C		
Fire class	Efl, E (according to EN 13501)		
Smoke class	S2		
Dimensional tolerances	Width / length / height +/- 2%, thickness +/- 5%		
Color	Black (minimal color deviations are possible due to the use of recycled rubber)		
Color retention	Colour may fade slightly overtime due to exposure to UV light		
Chemical resistance	Resistant to weak acids and alkalis. Conditionally resistant to oils		
Density	800 KG/m3		
Water permeability	565 mm per hour (according to EN 12616)		
Recycling	Products are fully recycleable		
Isolation	Rd 0,15 (according to EN 13165) / U 3,13 (according to EN 6946)		

Dimensions

Rubber tile carriers				
Article number	Sizes mm	Application		
729622	250 x 75 x 90	Rubber tile carrier ValkPro+	4	
729629	250 x 75 x 90	Rubber tile carrier ValkPro+ for PVC roofs	4	
729627	290 x 115 x 65	Rubber elevation block gravel roof ValkPro+		
729630	300 x 150 x 30	Rubber load distributor ValkPro+		
729631	300 x 150 x 30	Rubber load distributor ValkPro+ for PVC roofs		
729650	250 x 250 x 39	ValkBox3	4	

Application

 The rubber articles in the table above can be applied on bitumen, TPO, FPO and EPDM roofing. For PVC roofing, an extra barrier between the rubber and the PVC is required to prevent the extraction of plasticizers from the PVC. See next page for more information.







Datasheet Rubber components

Tile carrier (729629) for PVC roof roofing

Technical specifications

- Tile carrier 729629 is standard equipped with a plastic polypropylene (PP) tray on the underside, which forms a barrier between the rubber and the PVC roof covering. This prevents the risk of possible removal of plasticizers from the PVC.
- Approved by TÜV Rheinland for application on PVC roofing based on migration tests (according to KIWA BRL 1511 parts 1 and 4, section 6.11) and bending tests (according to KIWA BRL 1511 part 4, chapter 6.23, table 1a, row 6.23-14).



Image: Exploded view of article 729629

Protective layer for other rubber components on PVC roof roofing

Technical specifications

- Protective layer / underlay to prevent migration of softeners from PVC roof membrane.
- Synthetic membrane manufactured in TPO modified polyolefin, double colour sand-grey/black, obtained by co-extrusion, reinforced by polyster mesh.
- The sand grey layer offers a high resistance to weather influences and UV-light. The black layer offers a high punch resistance.
- TPO has an expected durability of at least 30 years and ha a high chemical resistance.

Specification table

Specifications protective layer				
	Material TPO - FLAGON EP/PR			
Thickness	mm	1,04 - 1,144		
Weight	kg/m²	0,99 - 1,09		
Tensile strength	N/5 cm	≥ 1100		
Elongation to break	%	≥ 15		
Tear resistance	N	≥ 300		
Resistance to impact	mm	≥ 450		
Cold bending	°C	≤ -40		
Hydrostatic pressure resistance	6 hours at 0,5 Mpa	Waterproof		
Dimensional stability	%	≤ 0,5		
Resistance to artificial weathering	UV	no surface cracking		
Resistance to static punching	kg	≥ 20		